

CETRIS® ECO BASIC

CETRIS® ECO BASIC is a cement-bonded particleboard with smooth naturally cement-grey surface. It is produced by pressing a mixture of wood chips (21% of weight), Portland cement (63% of weight), treated waste from the production of cement-bonded particle boards (4% by weight), water (10% of weight), hydrating additives (2% of weight); it is available in standard thicknesses of 30, 32, 34, 36, 38 and 40 mm. The basic size of the board is 3,350 x 1,250 mm. We deliver the boards cut to the sizes specified by the customer, with rounded edge or chamfered edge to 45° angle. The cement-bonded particleboard are used mainly as a construction material in cases where moisture resistance, strength, ecological and hygienic harmlessness are required at the same time. CETRIS® Boards do not contain either asbestos or formaldehyde; they are resistant to insects and mold exposure. Can provide sound insulation. The boards can be worked with conventional woodworking tools. When using CETRIS® BASIC boards, the composition of the board and its origin - cementitious material - must be respected. Particles of free lime contained in Portland cement may penetrate the surface of the slab and airborne carbonation and efflorescence may occur, which disturb the uniform appearance of the board surface. The surface of the boards is not uniform in colour, therefore claims for appearance reasons cannot be accepted.

Technical specifications:

basic size:	3,350 x 1,250 mm
board thicknesses:	30-32-34-36-38-40 mm
Bulk density:	1,150-1,500 kg/m ³
service: to customer's requirements.	cutting, edge cutting
Surface:	smooth
surface finish:	without surface finish

Table of basic physical and mechanical properties of CETRIS® cement-bonded particleboards:	Limit values according to standard	Mean values - real
Bulk density acc. to EN 323:	min. 1,000 kg/m ³	1,350-1,500 kg/m ³
Bending tensile strength acc. to EN 310	min. 9.0 N/mm ²	min. 11.5 N/mm ²
Modulus of elasticity acc. to EN 310	min. 4,500 N/mm ²	min. 6,800 N/mm ²
Tensile strength perpendicular to the board plane acc. to EN 319	min. 0.5 N/mm ²	min. 0.63 N/mm ²
Internal bond after cycling in a humid environment according to EN 321	min. 0.3 N/mm ²	min. 0.41 N/mm ²
Reaction to fire acc. to EN 13 501-1		B-s1, d0
Index of flame propagation along the surface acc. to the Czech standard ČSN 73 0863		i = 0 mm/min
Thickness swelling when stored in water for 24 hours	max. 1.5 %	max. 0.28 %
Thickness swelling after cycling in a humid environment according to EN 321	max. 1.5 %	max. 0.31 %
Linear expansion with changes in humidity from 35% to 85% at 23 °C according to EN 13 009		max. 0.122 %
Water absorption by the board when stored in water for 24 hours		max. 16 %
Thermal expansion coefficient acc. to EN 13 471		10 × 10 ⁻⁶ K ⁻¹
Coefficient of thermal conductivity acc. EN 12 664; thickness 8 to 40 mm		0.200 - 0.287 W/mK
Airborne sound insulation according to Czech standard CSN 73 0513, th.8 to 40mm		30 dB – 35 dB
Diffusion resistance factor according to DIN EN ISO 12572, th.8 to 40		52.8 – 69.2
Resistance to frost at 100 cycles according to EN 1328	R _L > 0.7	R _L = 0.97
pH of the board material		12,5
Mass activity Ra 226	150 Bq/kg	22 Bq/kg
Mass activity index	I = 0.5	I = 0.21
Surface resistance to water and chemical de-icing agents acc. to Czech standard CSN 73 1326	Waste after 100 cycles max. 800 g/m ² (Method A)	Waste after 100 cycles max. 20.4 g/m ² (Method A)
	Waste after 75 cycles max. 800 g/m ² (Method C)	Waste after 100 cycles max. 47.8 g/m ² (Method C)
Resistance to arc discharge of high voltage according to EN 61 621		th. 10mm, min.143 sec
Shearing friction coefficient acc. to the Czech standard ČSN 74 4507		Static μs = 0.73
		dynamic μd = 0.76
Mass balanced humidity at 20° and a relative humidity of 50% according to EN 634-1	9 ± 3 %	9.0%

Dimensional tolerance:

Feature	Board thickness	Requirement
Thickness of uncut board	30-40 mm	±1.5 mm
Length and width of the basic format	30-40 mm	±5.0 mm
Precision of cutting the length and width	30-40 mm	±3.0 mm
Edge straightness tolerance	30-40 mm	1.5 mm/m
Rectangularity tolerance	30-40 mm	2.0 mm/m

Appearance:

Parameter	I.Quality class	II.Quality class
Deviation from the right angle	max. 2 mm/1 m of length	max. 4 mm/1 m of length
Permitted edge damage	max. to the depth of 3 mm	max. to the depth of 30 mm
Protrusions on the surface	max.1 mm, size 10 mm	max. 1 mm
Depressions	max.1 mm, size 10 mm	max. 2 mm